

OLIVE WAX KERAGREEN MOLDED

Description: Molded Olive Wax

Characteristics:

	Unit Methods	Value
Freezing point °C	ASTM D938	°C 50-60
Melting point °C	ASTM D3954 °C	55-65
Viscosity @ 100°C	ASTM D445 cSt	9-16
Penetration @ 25°C	ASTM D1321 1/10mm	30-45
Colour	VISUAL	

Recommended Applications:

Manufacture of moulded candles.

It is a product used for the manufacture of decorative figures

Worked.

Properties:

Waxy solid of ivory color and neutral odor, presented in pearls.

Storage and preservation:

Protect from heat, water, dust and light. Although the temperature and humidity do not affect the safety of the product, they may however, affect its presentation and physical condition. It is recommended that Store in cool, dry places, at a temperature between 5°C and 25°C.

Presentation:

20 Kg boxes.

19 mai 2025

Active

Distribution C ompany

Phone: + 33 (0) 4 75 54 35 05

Email: contact@adc-solution.com

SIREN: 432 961 134 SIRET: 432 961 134 00041

40 Impasse des Jones D 126 route d'Allan 26780 Malataverne

ADC France with a capital of 163,200 Euros – RCS 432 961 134 VALENCE – VAT FR 64 432 961 134